

SID

Factory: Rot am See

Article:

ML10

Provided:

Customer:

Date:

03.04.2026

WÜRTH  
ELEKTRONIK  
MORE THAN  
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-035my 330x490mm	50200242	35	VS	 B00
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		35	L2	
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		
		35	L3	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		35	L4	
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		
		35	L5	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		35	L6	
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		
		35	L7	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		35	L8	
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		
		35	L9	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
A-RS Kupferfolie-035my 330x490mm	50200242	35	RS	

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

1428 µm

Version 1.2.20.35

© Würth Elektronik