

SID

Factory: Rot am See

Article:

ML10

Provided:

Customer:

Date:

03.04.2026

WÜRTH  
ELEKTRONIK  
MORE THAN  
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	146		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		18	L2	
C-RS-FR4-ML-0.254mm-018+018-TG150-HF-...	50203053	254		
		18	L3	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		18	L4	
C-RS-FR4-ML-0.254mm-018+018-TG150-HF-...	50203053	254		
		18	L5	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		18	L6	
C-RS-FR4-ML-0.254mm-018+018-TG150-HF-...	50203053	254		
		18	L7	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
		18	L8	
C-RS-FR4-ML-0.254mm-018+018-TG150-HF-...	50203053	254		
		18	L9	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	146		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	

Thickness after Pressing

B00:

1890 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2090 µm

Dmin:

1690 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2000 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2200 µm

Dmin:

1800 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

1905 µm

Version 1.2.20.35

© Würth Elektronik