

SID

Factory: Rot am See

Article:

ML12

Provided:

Customer:

Date:

03.04.2026



WÜRTH  
ELEKTRONIK  
MORE THAN  
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	B00
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	121	2	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	0	3	
		18	L2	
B-RS-FR4-ML-0.107mm-018+018-TG150-HF-...	50203004	107	4	
		18	L3	
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	114	5	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	0	6	
		18	L4	
B-RS-FR4-ML-0.107mm-018+018-TG150-HF-...	50203004	107	7	
		18	L5	
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	114	8	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	0	9	
		18	L6	
B-RS-FR4-ML-0.107mm-018+018-TG150-HF-...	50203004	107	10	
		18	L7	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	114	11	
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	0	12	
		18	L8	
B-RS-FR4-ML-0.107mm-018+018-TG150-HF-...	50203004	107	13	
		18	L9	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	114	14	
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	0	15	
		18	L10	
B-RS-FR4-ML-0.107mm-018+018-TG150-HF-...	50203004	107	16	
		18	L11	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B(...	50203000	121	17	
C-RAS-FR4-PP-106-H71-TG150-HF-EM-37B(...	50202996	0	18	
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

1449 µm

Version 1.2.20.35

© Würth Elektronik