

SID

Factory: Rot am See

Article:

ML16

Provided:

Customer:

Date:

24.04.2026



**WURTH
ELEKTRONIK**
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		2	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		3	
		35	L2		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		4	A01
		35	L3		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		5	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		6	
		35	L4		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		7	A02
		35	L5		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		8	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		9	
		35	L6		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		10	A03
		35	L7		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		11	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		12	
		35	L8		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		13	A04
		35	L9		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		14	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		15	
		35	L10		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		16	A05
		35	L11		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		17	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		18	
		35	L12		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		19	A06
		35	L13		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	124		20	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		21	
		35	L14		
C-RS-FR4-ML-0.107mm-035+035-TG150-HF-...	50203003	107		22	A07
		35	L15		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	139		23	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		24	
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	25	

B00

Thickness after Pressing B00: 2290 µm Tol+: 240 µm Tol-: 240 µm Dmax: 2530 µm Dmin: 2050 µm

Thickness over all 0 µm Tol+: 0 µm Tol-: 0 µm Dmax: 0 µm Dmin: 0 µm

Demand for customer Thickness (D): 2400 µm Tol+: 240 µm Tol-: 240 µm Dmax: 2640 µm Dmin: 2160 µm

Measuring point: (05) over SM and galv. Cu; both sides nominal: 2297 µm

Version 1.2.20.35

© Würth Elektronik