

SID

Factory: Rot am See

Article:

ML8

Provided:

Customer:

Date:

03.04.2026

WÜRTH
ELEKTRONIK
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-035my 330x490mm	50200242	35	VS	1
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	262		2
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		3
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		4
		35	L2	
C-RS-FR4-ML-0.610mm-035+035-TG150-HF-...	50203023	610		5
		35	L3	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	247		6
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		7
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		8
		35	L4	
C-RS-FR4-ML-0.610mm-035+035-TG150-HF-...	50203023	610		9
		35	L5	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	247		10
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		11
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		12
		35	L6	
C-RS-FR4-ML-0.610mm-035+035-TG150-HF-...	50203023	610		13
		35	L7	
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	262		14
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		15
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		16
A-RS Kupferfolie-035my 330x490mm	50200242	35	RS	17

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

3128 µm

Version 1.2.20.35

© Würth Elektronik