

SID

Factory: Rot am See

Article:

ML4

Provided:

Customer:

Date:

31.03.2026

WÜRTH
ELEKTRONIK
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	465		2		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		3		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		4		
		18	L2			
B-RS-FR4-DS-0.914mm-018+018-TG150-HF-...	50203008	878		5	A00	B00
		18	L3			
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	465		6		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		7		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		8		
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	9		

Thickness after Pressing

B00: 1890 µm Tol+: 200 µm Tol-: 200 µm Dmax: 2090 µm Dmin: 1690 µm

Thickness over all

0 µm Tol+: 0 µm Tol-: 0 µm Dmax: 0 µm Dmin: 0 µm

Demand for customer

Thickness (D): 2000 µm Tol+: 200 µm Tol-: 200 µm Dmax: 2200 µm Dmin: 1800 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal: 1880 µm

Version 1.2.20.35

© Würth Elektronik