

SID

Factory: Rot am See

Article:

ML6

Provided:

Customer:

Date:

03.04.2026

WÜRTH
ELEKTRONIK
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1	
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	381		2	
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		3	
		35	L2		
B-RaS-FR4-DS-0.991mm-035+035-TG150-HF...	50203141	920		4	A01
		35	L3		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	366		5	
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		6	B00
		35	L4		
B-RaS-FR4-DS-0.991mm-035+035-TG150-HF...	50203141	920		7	A02
		35	L5		
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	381		8	
A-RAS-FR4-PP-7628-H45-TG150-HF-EM-37B...	50203002	0		9	
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	10	

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

3144 µm

Version 1.2.20.35

© Würth Elektronik