

SID

Factory: Rot am See

Article:

ML8

Provided:

Customer:

Date:

03.04.2026

WÜRTH
ELEKTRONIK
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

| Material Text | Mat. Nr. | µm | Stackup | Process overview |
|---------------|----------|----|---------|------------------|
|---------------|----------|----|---------|------------------|

| | | | | | | |
|--|----------|-----|----|----|-----|-----|
| A-RS Kupferfolie-018my 330x490mm | 50200238 | 18 | VS | 1 | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 139 | | 2 | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 0 | | 3 | | |
| | | 35 | L2 | | | |
| C-RS-FR4-ML-0.508mm-035+035-TG150-HF-... | 50203006 | 508 | | 4 | A01 | |
| | | 35 | L3 | | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 124 | | 5 | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 0 | | 6 | | |
| | | 35 | L4 | | | |
| C-RS-FR4-ML-0.508mm-035+035-TG150-HF-... | 50203006 | 508 | | 7 | A02 | B00 |
| | | 35 | L5 | | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 124 | | 8 | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 0 | | 9 | | |
| | | 35 | L6 | | | |
| C-RS-FR4-ML-0.508mm-035+035-TG150-HF-... | 50203006 | 508 | | 10 | A03 | |
| | | 35 | L7 | | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 139 | | 11 | | |
| C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B... | 50203000 | 0 | | 12 | | |
| A-RS Kupferfolie-018my 330x490mm | 50200238 | 18 | RS | 13 | | |

Thickness after Pressing

B00:

2290 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2530 µm

Dmin:

2050 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2400 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2640 µm

Dmin:

2160 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

2296 µm

Version 1.2.20.35

© Würth Elektronik