

SID

Factory: Rot am See

Article:

ML8

Provided:

Customer:

Date:

23.04.2026

WÜRTH
ELEKTRONIK
MORE THAN
YOU EXPECT

Processtechnology: B: undefined

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	245		2		
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		3		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		4		
		105	L2			
C-RaS-FR4-ML-0.406mm-105+105-TG150-HF...	50203125	410		5		A01
		105	L3			
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	260		6		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		7		
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		8		
		105	L4			
C-RaS-FR4-ML-0.406mm-105+105-TG150-HF...	50203125	410		9		A02
		105	L5			B00
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	260		10		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		11		
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		12		
		105	L6			
C-RaS-FR4-ML-0.406mm-105+105-TG150-HF...	50203125	410		13		A03
		105	L7			
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	245		14		
C-RAS-FR4-PP-2116-H53-TG150-HF-EM-37B...	50203001	0		15		
C-RAS-FR4-PP-1080-H63-TG150-HF-EM-37B...	50203000	0		16		
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	17		

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) over SM and galv. Cu; both sides

nominal:

3010 µm

Version 1.2.20.35

© Würth Elektronik