

SID

Factory: Rot am See

Article:

625

ML4

Provided:

Stockburger, Olesja

Customer:

Date:

19.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-035my 330x490mm	50200242	35	VS	<div><div>1</div><div>2</div><div>3</div><div>4</div><div>5</div><div>6</div><div>7</div><div>8</div><div>9</div><div>10</div><div>11</div></div> <div>A00B00</div>
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	470		
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		
C-RS-FR4-ML-0.71mm-105+105-TG150-HF		105	L2	
	50200961	710		
		105	L3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	470		
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		
A-RS Kupferfolie-035my 330x490mm	50200242	35	RS	

Thickness after Pressing

B00:

1890 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2090 µm

Dmin:

1690 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2000 µm

Tol+:

200 µm

Tol-:

200 µm

Dmax:

2200 µm

Dmin:

1800 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1930 µm

Version 1.2.14.15

© Würth Elektronik