

SID

Factory: Rot am See

Article:

699

ML12

Provided:

Stockburger, Olesja

Customer:

Date:

02.02.2016



Processtechnology: B: undefiniert

| Material Text | Mat. Nr. | µm | Stackup | Process overview |
|-------------------------------------|----------|-----|---------|------------------|
| A-RS Kupferfolie-018my 330x490mm | 50200238 | 18 | VS | B00 |
| A-RS-FR4-Prepreg-106-TG150-HF | 50200640 | 109 | | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 0 | | |
| | | 35 | L2 | |
| A-RS-FR4-ML-0.10mm-035+035-TG150-HF | 50200647 | 100 | | |
| | | 35 | L3 | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 115 | | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 0 | | |
| | | 35 | L4 | |
| A-RS-FR4-ML-0.10mm-035+035-TG150-HF | 50200647 | 100 | | |
| | | 35 | L5 | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 110 | | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 0 | | |
| | | 35 | L6 | |
| A-RS-FR4-ML-0.10mm-035+035-TG150-HF | 50200647 | 100 | | |
| | | 35 | L7 | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 110 | | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 0 | | |
| | | 35 | L8 | |
| A-RS-FR4-ML-0.10mm-035+035-TG150-HF | 50200647 | 100 | | |
| | | 35 | L9 | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 115 | | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 0 | | |
| | | 35 | L10 | |
| A-RS-FR4-ML-0.10mm-035+035-TG150-HF | 50200647 | 100 | | |
| | | 35 | L11 | |
| A-RS-FR4-Prepreg-1080-TG150-HF | 50200641 | 109 | | |
| A-RS-FR4-Prepreg-106-TG150-HF | 50200640 | 0 | | |
| A-RS Kupferfolie-018my 330x490mm | 50200238 | 18 | RS | |

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1554 µm

Version 1.2.14.15

© Würth Elektronik