

SID

Factory: Rot am See

Article:

719

ML14

Provided:

Stockburger, Olesja

Customer:

Date:

15.02.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	240		2
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		3
		35	L2	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		4
		35	L3	
				A01
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	270		5
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		6
		35	L4	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		7
		35	L5	
				A02
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	225		8
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		9
		35	L6	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		10
		35	L7	
				A03
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	220		11
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		12
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		13
		35	L8	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		14
		35	L9	
				A04
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	225		15
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		16
		35	L10	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		17
		35	L11	
				A05
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	270		18
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		19
		35	L12	
A-RS-FR4-ML-0.15mm-035+035-TG150-HF	50200651	150		20
		35	L13	
				A06
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	240		21
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		22
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	23

B00

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

3046 µm

Version 1.2.14.15

© Würth Elektronik