

SID

Factory: Rot am See

Article:

510

ML6

Provided:

Kracht, Enrico

Customer:

Date:

10.08.2015



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	177		2	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		3	
A-RS-FR4-ML-0.41mm-018+018-TG150-HF	50200904	18	L2		A01
		410		4	
		18	L3		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	188		5	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		6	B00
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		7	
A-RS-FR4-ML-0.41mm-018+018-TG150-HF	50200904	18	L4		A02
		410		8	
		18	L5		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	173		9	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		10	
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	11	

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1466 µm

Version 1.2.14.15

© Würth Elektronik