

SID

Factory: Rot am See

Article:

642

ML4

Provided:

Stockburger, Olesja

Customer:

Date:

20.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
---------------	----------	----	---------	------------------

A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1	A00 B00
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	460		2	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		4	
C-RS-FR4-DS-2.00mm-070+070-TG150-HF	50200949	70	L2		
		1860		5	
		70	L3		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	460		6	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		7	
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		8	
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	9	

Thickness after Pressing

B00:

3090 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3410 µm

Dmin:

2770 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

3200 µm

Tol+:

320 µm

Tol-:

320 µm

Dmax:

3520 µm

Dmin:

2880 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

3060 µm

Version 1.2.14.15

© Würth Elektronik