

SID

Factory: Rot am See

Article:

678

ML8

Provided:

Stockburger, Olesja

Customer:

Date:

26.01.2016



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-070my 330x490mm	50200246	70	VS	1
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	267		2
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		3
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		4
B-RS-FR4-ML-0.20mm-070+070-TG150-HF	50200889	70	L2	5
		200		
		70	L3	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	275		6
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		7
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		8
B-RS-FR4-ML-0.20mm-070+070-TG150-HF	50200889	70	L4	9
		200		
		70	L5	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	275		10
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		11
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		12
B-RS-FR4-ML-0.20mm-070+070-TG150-HF	50200889	70	L6	13
		200		
		70	L7	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	267		14
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		15
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		16
A-RS Kupferfolie-070my 330x490mm	50200246	70	RS	17

Thickness after Pressing

B00:

2290 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2530 µm

Dmin:

2050 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2400 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2640 µm

Dmin:

2160 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

2244 µm

Version 1.2.14.15

© Würth Elektronik