

SID

Factory: Rot am See

Article:

581

ML10

Provided:

Landwehr, Melanie


Customer:

Date:

17.12.2015



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	220		
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		
		18	L2	
A-RS-FR4-ML-0.10mm-018+018-TG150-HF	50200646	100		
		18	L3	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	165		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		
		18	L4	
A-RS-FR4-ML-0.10mm-018+018-TG150-HF	50200646	100		
		18	L5	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	120		
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		
		18	L6	
A-RS-FR4-ML-0.10mm-018+018-TG150-HF	50200646	100		
		18	L7	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	161		
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		
		18	L8	
A-RS-FR4-ML-0.10mm-018+018-TG150-HF	50200646	100		
		18	L9	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	220		
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	

Thickness after Pressing

B00:

1440 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1595 µm

Dmin:

1285 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

1550 µm

Tol+:

155 µm

Tol-:

155 µm

Dmax:

1705 µm

Dmin:

1395 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

1466 µm

Version 1.2.14.15

© Würth Elektronik