

SID

Factory: Rot am See

Article:

514

ML6

Provided:

Kracht, Enrico

Customer:

Date:

10.08.2015



Processtechnology: B: undefiniert

Material Text	Mat. Nr.	µm	Stackup	Process overview
A-RS Kupferfolie-018my 330x490mm	50200238	18	VS	1
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	220		2
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		3
A-RS-FR4-ML-0.71mm-018+018-TG150-HF	50200793	18	L2	4
		710		
		18	L3	
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	310		5
A-RS-FR4-Prepreg-7628-TG150-HF	50200643	0		6
A-RS-FR4-Prepreg-1080-TG150-HF	50200641	0		7
A-RS-FR4-ML-0.71mm-018+018-TG150-HF	50200793	18	L4	8
		710		
		18	L5	
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	220		9
A-RS-FR4-Prepreg-2116-TG150-HF	50200642	0		10
A-RS Kupferfolie-018my 330x490mm	50200238	18	RS	11

B00

Thickness after Pressing

B00:

2290 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2530 µm

Dmin:

2050 µm

Thickness over all

0 µm

Tol+:

0 µm

Tol-:

0 µm

Dmax:

0 µm

Dmin:

0 µm

Demand for customer

Thickness (D):

2400 µm

Tol+:

240 µm

Tol-:

240 µm

Dmax:

2640 µm

Dmin:

2160 µm

Measuring point: (05) über LM und galv.Cu; beidseitig

nominal:

2278 µm

Version 1.2.14.15

© Würth Elektronik